EF601

Low Density Polyethylene

Application/Uses

- Heavy duty bags
- Heavy duty shipping sacks
- Industrial shrink film
- Heavy duty C&A sheeting

Product Description

Westlake EF601 is a fractional melt LDPE with excellent toughness. It is suggested in heavy duty films and shipping sacks, and in industrial shrink applications. It can be used as a bubble stabilizer in LLDPE rich films.

| Typical Physical Properties | | | |
|--|----------------|---|--|
| <u>Property</u> | | Test Method | Typical Value, Units |
| Melt Index *Density Dart Impact Coefficient of Friction Ultimate Tensile Ultimate Elongation | MD TD MD | D 1238 D 1505 D 1709 D 1894 D 882 D 882 D 882 D 882 | 0.25g/10 min 919 kg/m³ (0.919 g/cm³) 250 g/mil 0.5 3,500 psi 2,700 psi 250 % |
| 1% Secant Modulus | TD MD TD | D 882 D 882 D 882 | 750 % 22,000 psi 28,000 psi |

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

NOTES

Test specimens for blown film: nominal thickness 2.0 mils; blow up ratio 2.5:1, die gap 35 mils.

FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

PROCESSING

Melt temperatures of 360° F – 400° F are recommended for Westlake EF601 with blow-up ratios of 1.5:1 or higher.

COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

WESTLAKE CHEMICAL CORPORATION

2801 Post Oak Blvd Suite 600 Houston, Texas Customer Service: 1-800-545-9577

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.